



Technical Data Sheet



PRODUCT NAME

Zebracoat

ISSUE DATE

3/3/2021

PART NUMBER

ZEB148



PRODUCT DESCRIPTION

Zebracoat is specifically developed to adhere to uPVC substrates to renovate window frames, conservatories and doors. This product was also designed to be "Ready for Use", allowing it to be applied straight from the tin by spray applying.

Zebracoat performs very well when coating window frames, reducing the risk of window seals adhering to the coating.



PRODUCT PROPERTIES

Zebracoat is also available in a limited colour range with special heat reflective pigmentation, please ask for further details.



MAXIMUM VOC CONTENT

- 0.745kgs/ltr

REGULATIONS / COMPLIANCE

- 2004/42 IIB (E) 840



TECHNICAL INFORMATION

COVERAGE 10.5 square metres per litre @ 20 microns dft (Theoretical)

FLASHPOINT -6°C

STORAGE Store between 5°C - 25°C. When not in use, cans must be kept sealed



CLEANING

Ensure surfaces to be coated are dry and must be cleaned using the appropriate product to remove all traces of contaminants.



HEALTH AND SAFETY

- Refer to SDS and tin label prior to use.
- Suitable respiratory equipment should be worn when spraying.


APPLICATION METHODS

AEROSOL

COMPLIANT SPRAY GUN

BRUSH

PRESSURE POT



MIXING RATIO

RFU		Base Thinner	RFU Up to 20%	Base	RFU	Base	RFU
-----	--	-----------------	------------------	------	-----	------	-----



VISCOSITY

	25-30 seconds B4 cup		25-30 seconds B4 cup
--	----------------------	--	----------------------




SPRAY GUN SETUP

	1.1-1.4		1.1-1.4
--	---------	--	---------



NUMBER OF COATS

1-2 full coats	1-2 full coats	1 coat	1-2 full coats
----------------	----------------	--------	----------------



FLASH OFF

10-15 mins between coats	10-15 mins between coats	10-15 mins between coats	10-15 mins between coats
--------------------------	--------------------------	--------------------------	--------------------------



DRYING TIME

Touch dry Hard dry	10-15mins @20°C 45-60mins @20°C	Touch dry Hard dry	10-15mins @20°C 45-60mins @20°C	Touch dry Hard dry	10-15mins @20°C 45-60mins @20°C	Touch dry Hard dry	10-15mins @20°C 45-60mins @20°C
-----------------------	------------------------------------	-----------------------	------------------------------------	-----------------------	------------------------------------	-----------------------	------------------------------------



RECOATABILITY / OVERCOATING

Maximum 8 hours without the need for flatting



WET FILM THICKNESS

100 microns	100 microns	100 microns	100 microns
-------------	-------------	-------------	-------------



DRY FILM THICKNESS

20-25 microns	20-25 microns	20-25 microns	20-25 microns
---------------	---------------	---------------	---------------

This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is to the best of Zebracoat's knowledge and believed accurate and reliable as of the date indicated. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy themselves as to the suitability and completeness of such information for their own particular use. For professional use only.